

umicore

RHODUNA® DIAMOND BRIGHT RHODIUM ELECTROLYTE



Brilliant-White and Ultra-Bright Rhodium Coatings

RHODUNA® Diamond Bright deposits brilliant-white, ultra-bright coatings of previously unattained lightness and brilliance. It is additionally characterized by high covering speed and excellent throwing power. Furthermore the RHODUNA® Diamond Bright layer thicknesses of up to 5 µm can be deposited crack-free.

Rhodium can be directly deposited on silver, gold, copper and copper alloys, nickel and nickel alloys. The layers are extremly low-porous and therefore very corrosion resistant.



Advantages

- Ultra-bright coatings with previously unattained lightness and brilliance
- Good covering speed
- Minor porosity
- Excellent throwing power
- Layer thicknesses of up to 5 µm can be deposited
- For rack and barrel plating
- High abrasion resistance

Applications

- Jewellery
- Watches
- Spectacle frames
- Writing implements
- Technical applications (reed contact)

RHODUNA[®] DIAMOND BRIGHT **RHODIUM ELECTROLYTE**



Electrolyte characteristics	
Electrolyte type	Strongly acidic
Metal content	2 (1.6 - 3.0) g/l Rh
pH value	< 1
Operating temperature	40 (RT - 65) °C
Current density range	1 - 2 (0.5 - 10) A/dm²
Plating speed	0.08 µm/min at 1 A/dm ² 0.10 µm/min at 2 A/dm ²
Anode material	Pt-Ti (type PLATINODE® Pt/Ti) or MMO (type PLATINODE® 187)

Coating characteristics

Coating	Rhodium
Purity	99.99 wt. % Rh
Colour of deposit	Brilliant-white
Brightness	Ultra-bright
Hardness of deposit HV 0.015 (Vickers) approx. values	Approx. 800 - 900 HV
Max. coating thickness	Approx. 3 - 5 µm
Density of the coating	Approx. 12.4 g/cm ³

Abrasion According to Bosch-Weinmann



Colour Measurement (CIE-L*a*b*) Rhodium Electrolytes



cal rhodium electrolytes

Thick Layers

Layer thickness: ca. 4 µm Edge: ca. 6 µm Many pores.



Layer thickness: ca. 4 µm Edge: ca. 6 µm Almost no pores.

YOUR CONTACT

Do you have a specific question or would you like a no-obligation quote calculation? Our specialist will be happy to help you with any technical questions you might have.



Markus Legeler

Mail:

Manager Sales International

markus.legeler@eu.umicore.com Phone: +49 (0) 7171 607 - 204



The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.

mds.umicore.com