

PHP-900 IR-10FE

PERMANENT HOLE PLUGGING INK



TECHNICAL SPECIFICATIONS

All technical data is taken from information from the manufacturer San-Ei Kagaku Co, Ltd., Japan.

Material Properties		
Item	Data	Notes
Viscosity	35±5 Pa·s	VISCONTESER VT-04, 25 °C
Particle size	Less than 15 micron	JIS K5600-2-5
Density	1.74	JIS K5600-2-4
Shelf life	4 months	Below 10 °C
Pot life	7 days	at 25 °C, 60 % RH
Halogen content	Total Cl: Less than 900 ppm Total Br: Less than 900 ppm Total Cl + Br: Less than 1500 ppm	JPCA-ES01-2003
RoHS standard	Passed	Cd, Pb, Hg, Cr6+, PBBs, PBDEs
Cure condition	110 °C, 60 min + 150 °C, 30 min	Box type oven

Thermal Properties		
Item	Data	Notes
Tg	158 °C	TMA, JPCA-BU01-1998
β1	38 ppm	TMA, JPCA-BU01-1998
β2	89 ppm	TMA, JPCA-BU01-1998
Young's modulus	8100 MPa	DMA, 30 °C
Tensile strength	40 MPa	JIS K7113, 23 °C
Elongation	0.7 %	JIS K7113, 23 °C
Tensile modulus	10 GPa	JIS K7113, 23 °C
Passion's ratio	0.320	JIS K7113, 23 °C
Thermal conductivity	0.642 W/mK	Laser flash method

PHP-900 IR-10FE

PERMANENT HOLE PLUGGING INK

TECHNICAL SPECIFICATIONS

All technical data is taken from information from the manufacturer San-Ei Kagaku Co, Ltd., Japan.

Heat Resistance		
Item	Data	Notes
Solderability	No blister, no crack	288 °C, 60 sec
Heat cycle	No blister, no crack	288 °C, 10 sec, 5 cycles
1 % weight loss temperature	360 °C	TG/DTA
Peel strength	>9 N/cm	Cu plating thickness: 20 µm

Chemical Properties		
Item	Data	Notes
Water absorption	0.18 %	JIS C6481
Resistance to chemicals		
10 wt% Sulfuric acid	No blister, no crack	RT, 60 min
10 wt% Caustic soda	No blister, no crack	RT, 60 min
IPA	No blister, no crack	RT, 60 min
Dichloromethane	No blister, no crack	RT, 60 min
Acetone	No blister, no crack	RT, 60 min
Boiling water	No blister, no crack	100 °C, 60 min

TECHNICAL SPECIFICATIONS

All technical data is taken from information from the manufacturer San-Ei Kagaku Co, Ltd., Japan.

Electrical Properties		
Item	Data	Notes
Dielectric constant	5.55	ASTM D150, 1 MHz
Dissipation factor	0.0164	ASTM D150, 1 MHz
Surface resistivity	7.0E+15 ohm	ASTM D257
Volume resistivity	6.0E+14 ohm · cm	ASTM D257
Breakdown voltage	15.5 kV/mm	ASTM D149

ANSPRECHPARTNER

Sie haben tiefergehende Fragen oder wünschen eine unverbindliche Angebotskalkulation?
Unsere Fachleute helfen Ihnen, natürlich auch bei technischen Fragen, gerne weiter.



Andrea Grau
Leiterin Vertrieb Europa

E-Mail: andrea.grau@eu.umicore.com
Telefon: +49 (0) 7171 607 - 229

