

AURUNA® 311 GOLD COBALT ELECTROLYTE



For the Adhesive Direct Gold-Plating of Stainless Steel and Nickel

AURUNA® 311 is a strongly acidic alloy electrolyte for the adhesive direct gold-plating of stainless steel. It is preferably used for chromium-nickel steels, molybdenum steels and nickelbased alloys difficult to activate. Due to its strong activation effect, the electrolyte can be often successfully used as well for other passive materials difficult to plate.

The gold electrolyte is suitable for both strike gold layers and thick coatings in the decorative field. The coatings are ductile, low in pores and protect against corrosion. The alloy electrolyte can be used for rack and barrel operation as well as in reel-to-reel plating (e.g. spray and dip cells and brush).

AURUNA® 311 is also available as a cobalt-free special version.



Advantages

- Hard gold electrolyte for the direct gold-plating of stainless steel
- $\cdot\,$ Very good activation effect without halogenides
- Low-pore, ductile and crack-free coatings
- Suitable for strike gold layers as well as for thick coatings
- $\cdot \,$ Good throwing power
- Available as a cobalt-free special version
- The coatings are RoHS compliant
- Suitable for rack, barrel and reel-to-reel plating

Applications

• Household articles

umicore

Electroplating

- Writing implements
- Spectacle frames
- Watches
- Cutlery

AURUNA® 311 **GOLD COBALT ELECTROLYTE**

TECHNICAL SPECIFICATIONS

Electrolyte characteristics	
Electrolyte type	Strongly acidic
Metal content	2 (1.0 - 2.5) rsp. 4 (3.5 - 4.5) g/l Au
pH value	0.6 (0.1 - 0.8)
Operating temperature	Room temperature up to max. 40 °C
Current density range	2 - 6 A/dm²
Plating speed	0.04 - 0.15 µm/min
Anode material	Pt-Ti, MMO (type PLATINODE® 177)



Coating characteristics	
Coating	Gold-cobalt
Alloy composition, approx. values	0.3 weight % Co 99.7 weight % Au
Colour of deposit	Deep yellow
Brightness	Bright
Hardness of deposit HV 0.015 (Vickers) approx. values	165 HV
Max. coating thickness	Approx. 10 µm
Density of the coating	Approx. 17.5 g/cm ³

YOUR CONTACT

Do you have a specific question or would you like a no-obligation quote calculation? Our specialist will be happy to help you with any technical questions you might have.



Markus Legeler Manager Sales International

Mail:

markus.legeler@eu.umicore.com Phone: +49 (0) 7171 607 - 204



The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.

www.ep.umicore.com