



## **ARGUNA® ET-S Fine Silver Electrolyte**

# High-speed electrolyte for reel-to-reel plating

The ARGUNA® ET-S silver electrolyte is an alkaline-cyanide process specifically developed for use in high-speed equipment for reel-to-reel silver plating (using flow or spray technologies). The process deposits smooth and fine-grained, semi-bright coatings which are particularly suitable for semiconductor technology.

Current density and plating speed depend on the electrolyte agitation at the parts, i.e. on the equipment used. High flow velocities allow very high current densities.

#### **Electrolyte characteristics**

Electrolyte type	alkaline-cyanide
Metal content	100 g/l Ag
pH value	12.5
Operating temperature	30 - 75 °C (optimum 35 °C)
Current density range	10 - 150 A/dm²
Plating speed	0.2 - 1.5 μm/s
Anode material	Fine silver or MMO (type PLATINODE® 167 or 177)
Electrical conductivity	>50 m*(Ω*mm²)-1

### **Coating characteristics**

Coating	Fine silver
Purity	99.9 wt.% Ag
Colour of deposit	White
Brightness	Semi-bright
Hardness	110 HV (as plated)
1/2	



#### Advantages

- High-speed electrolyte for all-over and selective deposition of fine silver
- For reel-to-reel plating using flow or spray technologies
- Semi-bright coatings with very good soldering and bonding properties
- Use of soluble anodes possible

#### Applications

Contact surfaces for electrical and electronic components

#### Your contact person



Manager Sales International T: +49 7171 607 204 F: +49 7171 607 316 markus.legeler@eu.umicore.co m