

Al₂O₃ 99.98% Ø12.5x7mm 500g - 0481229

Specifications

Coating material	Aluminium oxide
Purity	99.98%
Form	Tablet
Dimensions	Ø 12.5 x 7 mm
Quantity	500 g
Theoretical density at 20°C in g/cm ³	~ 4.0
Melting point in °C	2000-2072

Temperature at vapor pressure

10 ⁻² mbar in °C	2050
10 ⁻¹ mbar in °C	2200
Boiling point in °C	2920-3040

Type of evaporation

Melting	Good
---------	------

Evaporation source (typically)

E-gun

Boat

Boat material

Mo	Good
----	------

Specific evaporation conditions

Preparation of base melt (pre-melt)	Good
Reactive gas pressure	Good

Substrate temperature range

100 - 200 °C	Good
200 - 300 °C	Good

Film transparency

Low	~ 0.19
High	~ 7

Film refractive index n / extinction coefficient k

at 550 nm: n	1.60-1.68
--------------	-----------