

Cr 99.95% 1.5-3.5mm 500g - 0711745-00500G

Specifications

| Coating material | Chromium |
|--|--------------|
| Purity | 99.95% |
| Form | Granulate |
| Dimensions | 1.5 - 3.5 mm |
| Quantity | 500 g |
| Theoretical density at 20°C in g/cm ³ | 7.2 |
| Melting point in °C | 1907 |

Temperature at vapor pressure

| 10 ⁻² mbar in °C | 1330 |
|-----------------------------|------|
| 10 ⁻¹ mbar in °C | 1470 |
| Boiling point in °C | 2672 |

Type of evaporation

| Sublimation | Good | |
|-------------|------|--|
| | | |

Evaporation source (typically)

| E-gun | | |
|---------------------------|----------|--|
| Directly from Cu crucible | Possible | |
| | | |
| Boat | | |
| Boat material | | |
| W | Good | |

Specific evaporation conditions

Low residual pressure

Good

Good

Reactive gas pressure

Film refractive index n / extinction coefficient k

| at 550 nm: n | 3.18 |
|--------------|---------------|
| at 550 nm: k | 4.41 |
| at 10 μm: n | 15.3 |
| at 10 µm: k | 26.4(8.86 μm) |

| - | |
|-------|----------|
| Ann | lication |
| 1 YPP | neacion |

Adhesion promotion