

ITO 90/10 99.99% 3.0-6.0mm 500g - 0703922

Specifications

Coating material	ITO 90/10 %
Purity	99.99%
Form	Granulate
Dimensions	3.0 - 6.0 mm
Quantity	500 g
HazardPictogram	GHS08
Statement	Warning
Theoretical density at 20°C in g/cm ³	7.1 (In ₂ O ₃ :SnO ₂ ratio 90:10)
Melting point in °C	1730

Temperature at vapor pressure

10 ⁻² mbar in °C	~ 700
-----------------------------	-------

Type of evaporation

Sublimation	Good
-------------	------

Evaporation source (typically)

E-gun

Directly from Cu crucible	Good
---------------------------	------

Liner material

Mo	Good
----	------

Boat

Boat material

W	Possible
---	----------

Mo	Good
----	------

Specific evaporation conditions

Low residual pressure	Good
Reactive gas pressure	Possible

Substrate temperature range

100 - 200 °C	Good
200 - 300 °C	Good

Ion or plasma assistance

possible	Possible
----------	----------

Film transparency

Low	~ 0.4
High	~ 1.1

Film refractive index n / extinction coefficient k

at 550 nm: n	1.90-2.00
--------------	-----------

Application	Transparent conductive film
-------------	-----------------------------