

Si 99.999% Ø21x5mm 5pcs - 0481619

Specifications

Coating material	Silicon
Purity	99.999%
Form	Discs
Dimensions	Ø 21 x 5 mm
Quantity	5 pcs
Theoretical density at 20°C in g/cm ³	2.3
Melting point in °C	1410

Temperature at vapor pressure

10 ⁻² mbar in °C	1630
10 ⁻¹ mbar in °C	1830
Boiling point in °C	2355

Type of evaporation

Melting	Good
---------	------

Evaporation source (typically)

E-gun

Directly from Cu crucible	Good
---------------------------	------

Boat

Boat material

W	Possible
Mo	Good

Specific evaporation conditions

Preparation of base melt (premelt)	Good
------------------------------------	------

Low residual pressure	Good
Reactive gas pressure	Possible

Substrate temperature range

100 - 200 °C	Good
--------------	------

Film transparency

Low	1
High	8

Film refractive index n / extinction coefficient k

at 550 nm: n	3.9(1 μm)
at 10 μm: k	3.4(3 μm)