

Ti3O5 99.9% 0.7-2.0mm 500g - 0484884

Specifications

Coating material	Titanium (III/IV)-oxide
Purity	99.9%
Form	Granulate
Dimensions	0.7 - 2.0 mm
Quantity	500 g
Theoretical density at 20°C in g/cm ³	4.0-4.2
Melting point in °C	1760

Temperature at vapor pressure

10 ⁻² mbar in °C	1980
10 ⁻¹ mbar in °C	2100

Type of evaporation

Melting	Good
---------	------

Evaporation source (typically)

E-gun

Boat

Boat material

W	Possible
Mo	Good

Specific evaporation conditions

Preparation of base melt (premelt)	Possible
Reactive gas pressure	Good

Substrate temperature range

< 100 °C	Good
100 - 200 °C	Good
200 - 300 °C	Good

Ion or plasma assistance

possible	Good
----------	------

Film transparency

Low	0.4
High	> 8

Film refractive index n / extinction coefficient k

at 550 nm: n	2.07-2.50
--------------	-----------