

Y2O3 99.99% Ø9.5x5mm 500g - 0481569

Specifications

Coating material	Yttrium oxide
Purity	99.99%
Form	Tablet
Dimensions	Ø 9.5 x 5 mm
Quantity	500 g
Theoretical density at 20°C in g/cm ³	5.0
Melting point in °C	2410

Temperature at vapor pressure

10 ⁻² mbar in °C	~ 2300
10 ⁻¹ mbar in °C	~ 2700
Boiling point in °C	4300-4440

Type of evaporation

Melting	Possible
Sublimation	Possible

Evaporation source (typically)

E-gun

Liner material	
W	Good

Boat

Boat material	
W	Possible
Mo	Good

Specific evaporation conditions

Preparation of base melt (premelt)	Possible
Reactive gas pressure	Good

Substrate temperature range

100 - 200 °C	Good
200 - 300 °C	Good

Film transparency

Low	< 0.25
High	10-12

Film refractive index n / extinction coefficient k

at 550 nm: n	1.78-1.87
--------------	-----------